



**HAL**  
open science

# Raman spectroscopy of adsorbed water in clays: first attempt of band assignment

Dominique de Ligny, Emmanuel Guillaud, Hélène Gailhanou, Philippe Blanc

► To cite this version:

Dominique de Ligny, Emmanuel Guillaud, Hélène Gailhanou, Philippe Blanc. Raman spectroscopy of adsorbed water in clays: first attempt of band assignment. *Procedia Earth and Planetary Science*, 2013, Proceedings of the Fourteenth International Symposium on Water-Rock Interaction, WRI 14, 7, pp.203-206. 10.1016/j.proeps.2013.03.202 . hal-00838526

HAL Id: hal-00838526

<https://brgm.hal.science/hal-00838526>

Submitted on 15 Dec 2020

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

## Water Rock Interaction [WRI 14]

# Raman spectroscopy of adsorbed water in clays: first attempt at band assignment

Dominique de Ligny<sup>a\*</sup>, Emmanuel Guillaud<sup>a</sup>, H  l  ne Gailhanou<sup>b</sup>, Philippe Blanc<sup>b</sup>

<sup>a</sup>*Institut Lumière Matière, CNRS, Université Lyon 1, 12 rue Ada Byron, 69622 Villeurbanne, France*

<sup>b</sup>BRGM, Service D3E, 3 avenue Claude Guillemin, 45000 Orléans, France

## Abstract

Raman spectroscopy can be a useful tool to determine water content within clays, or even in highly saturated solutions. The following assignment is proposed for the OH region of SAz-2: the two large bands at 3260 and 3475  $\text{cm}^{-1}$  are assigned to water in pores, the first one to water molecules coordinated to the interlayer cations, and the second one to structural Al-OH groups. The band at 3600  $\text{cm}^{-1}$  is therefore more likely related to adsorbed water on the clay surface. Simple intensity ratios of these different bands give good estimates of water content.

© 2013 The Authors. Published by Elsevier B.V. Open access under [CC BY-NC-ND license](#).

Selection and/or peer-review under responsibility of the Organizing and Scientific Committee of WRI 14 – 2013

**"Keywords: smectite, adsorbed water, Raman spectroscopy;"**

## 1. Introduction

Water in clays is a key issue for geology as well as material sciences. Indeed departure of adsorbed water from clays in sedimentary basin probably regulates the smectite to illite transition. It then plays a key role in reservoir formation as well as petroleum maturation. In the industrial side, especially in waste management, clays are used as active barrier that tend to prevent spreading of toxic elements in the environment. Water availability and its diffusion within the clay are here essential to understand how such barriers can be efficient.

Structure of water in clays is difficult to study for many aspects. First, it evolves rapidly with water partial pressure. Secondly usual techniques of structure determination as X-ray are not sensitive to hydrogen position. Vibrational spectroscopies are therefore used in the frequency range of OH bond

\* Corresponding author. Tel.: +33-472448568; fax: +33-472431130.

*E-mail address:* dominique.de-ligny@univ-lyon1.fr

vibrations around  $3500\text{ cm}^{-1}$ . Mainly infra-red spectroscopy (IR) and NMR were used until now [1-3]. Raman spectroscopy is a vibrational spectroscopy complementary to IR but with different selection rules more restrictive and therefore presenting sharper vibration band than IR. Even very sensitive to luminescence, Raman spectroscopy was rarely used to study hydrous minerals because often such emissions mask the Raman spectra. Using a UV laser as excitation source we were able to overcome this last restriction and to present here a first set of data on a smectite sample.

Water is present in clays in a variety of form. First it is a constitutive of the mineral itself, and OH groups can be found in the octahedral sheets. It can be also present in three different ways inside clays: in pores, adsorbed on clay surfaces or between layers, especially around exchangeable cations. All these OH groups contribute to the vibrational bands around  $3500\text{ cm}^{-1}$ . The first goal of this paper is to give some keys to constrain OH band assignment, preliminary to any later understanding of OH structure in clays. A study of OH in highly saturated salt solution is also presented as a possible analogous of the hydration sphere around the interlayer cation.

## 2. Materials and methods

The sample studied is the SAz-2 from the Clay Mineral Society. It is from Cheto Arizona. The structural formula taken from [4] is  $(\text{Ca}_{.39}\text{Na}_{.36}\text{K}_{.02})[\text{Al}_{2.71}\text{Mg}_{1.11}\text{Fe(III)}_{.12}\text{Mn}_{.01}\text{Ti}_{.03}][\text{Si}_{8.00}]\text{O}_{20}(\text{OH})_4$ . The interlayer cation is therefore mainly calcium with an interlayer charge of -1.08. The sample was only dispersed in distilled water and equilibrated at different relative humidity using saturated solution of various salts [5] or dried in air.

In order to see the effect of cation solvation by water, solutions were prepared by dissolving weighted NaOH crystals in 4ml of distilled water. The concentrations of this set of solutions range from 2 to 50 wt.% by 4 wt.% steps.

A micro-spectrometer Raman Horiba Jobin Yvon® LabRAM Aramis was used to collect the spectra. To prevent luminescence a laser UV HeCd by Kimmon® at 325 nm was used in association with a 2400 l/cm grating. Nevertheless some luminescence was still present from time to time. Its effect was removed by baseline subtraction in the  $2750$  to  $3900\text{ cm}^{-1}$  range using a polynomial function of degree 5 with the labspec software. This data reduction has no effect on band frequency position.

## 3. Results and discussion

### 3.1. Clay versus free water




Fig. 1. Raman spectra of (a) liquid water and (b)SAz-2. The position of the Gaussian fit is reported on the graphs.

In Figure 1 we compare the spectra obtained on free water and on SAz-2. In order to identify the different bands, the curve fitting of the Raman spectra by several Gaussian curves is shown. The number of bands in liquid water changes depending of the authors. A deconvolution in four bands, in agreement with [6], was used because it reproduces well the global spectra with the fewer contributions. The band at  $3218\text{ cm}^{-1}$  is assigned to symmetrical stretching of the OH bond inside a tetra-coordinated structure, and the band at  $3425\text{ cm}^{-1}$  to the asymmetric one [6]. The two other bands are not yet consensually assigned.

In the clay the two lower bands are roughly at the same frequency than liquid water and they correspond to water molecule in a tetra-coordinated arrangement probably in pore structures. The three narrower high frequency bands are intrinsic to the clay. In muscovite a unique contribution at  $3660\text{ cm}^{-1}$  is assigned unambiguously to hydroxyl group linked to Al octahedra. However, IR measurements show Fe-OH at  $3604\text{ cm}^{-1}$  and Al-OH or Mg-OH around  $3619\text{ cm}^{-1}$  [3,7]. To overcome this ambiguity measurements have been performed on solutions saturated in NaOH.

### 3.2. O-H vibration in highly saturated solution




Fig. 2. (a) Raman spectra for the NaOH solution at 17.2 wt.%. (b) Evolution of the Raman spectra for increasing concentration of NaOH, the spectra are normalized at  $3618\text{ cm}^{-1}$ . (c) Intensity ratio between the intensity at  $3618\text{ cm}^{-1}$  (OH associated with sodium cation) and at  $3461\text{ cm}^{-1}$  (antisymmetric stretching of pure water) versus the NaOH concentration.

In the interlayer domain water is often considered to form hydration sphere around the charge compensator cation [8-9]. This structure therefore should not be very far from cation concentrated solutions. In figure 2, the effect of the concentration in a NaOH solution is shown. It can be clearly recognized the two main bands of water which decrease quickly when cation concentration evolves. At high frequency two sharp peaks are present at  $3597$  and  $3618\text{ cm}^{-1}$  and can be assigned to the interaction between OH and sodium cation. Even if free water had a band at  $3620\text{ cm}^{-1}$ , the band width in NaOH is much narrower making the two contributions very distinct. This is confirmed by the very good correlation presented in fig. 2c. In the future this correlation could be used to measure the chemical concentration of water by Raman spectroscopy.

At very high concentration new bands appear at lower frequency and were assigned to  $\text{H}_3\text{O}_2^+$  due to  $\text{OH}^-$  transformation [10]. No such bands were ever observed in clays even at very low Relative Humidity since no pH variation is taking place in the interlayer.

### 3.3. Evolution with the Relative Humidity

Concerning the evolution of interlayer water with relative humidity, two approaches were investigated. One consisted in a direct drying of a drop of clay suspension and therefore recording the spectra evolution with time (Fig 3 a-b). The second consisted to equilibrate the clay with different saturated salt solutions (Fig 3 c). In both cases using the area ratio between the free water contribution below  $3535\text{ cm}^{-1}$  and the total area of the OH region, a good evaluation of the water content was possible. At very low Relative

Humidity the only contribution still present is that one at  $3660\text{ cm}^{-1}$ . Since no more removable water is present in the sample, this last band can be assigned to vibration of Al-OH and Mg-OH groups inside the octahedral layer in agreement with muscovite data.




Fig. 3. Evolution of the Raman spectra in the OH region with the relative humidity.

#### 4. Conclusion

The following assignment is proposed for the OH region of SAz-2: the two large bands at  $3260$  and  $3475\text{ cm}^{-1}$  are assigned to water in pores, and the band at  $3620\text{ cm}^{-1}$  to water molecules coordinated to the interlayer cations. The band at  $3600\text{ cm}^{-1}$  is therefore more likely connected to adsorbed water on the clay surface.

#### Acknowledgements

The authors thank Prof. Pierpaolo Zuddas for fruitful discussions and moral support. This study had also a very strong and knowledgeable input from Prof. Micheline Boudeulle; we warmly thank her.

#### References

- [1] Delville A, Grandjean J, Laszlo P. Order acquisition by clay platelets in a magnetic field. NMR study of the structure and microdynamics of the adsorbed water layer *J Phys Chem* 1991; **95**: 1383–1392.
- [2] Pel L, Kopinga K, Bertram G, Lang G. Water absorption in a fired-clay brick observed by NMR scanning. *J Phys D: Appl Phys* 1995; **28**: 675.
- [3] Vantelon D, Pelletier M, Michot L, Barres O, Thomas F. Fe, Mg and Al distribution in the octahedral sheet of montmorillonites. an infrared study in the OH-bending region. *Clay Minerals* 2001; **36**:369–379.
- [4] Van Olphen H, Fripiat JJ. *Data Handbook for Clay Minerals and Other Non-metallic Minerals*, Pergamon Press, Oxford and Elmsford; New York, 1979.
- [5] Lide D, *Handbook of chemistry and physics*, 78th edition, CRC Press, 1997.
- [6] Murphy W, Bernstein H. Raman spectra and an assignment of the vibrational stretching region of water. *Journal of physical chemistry*. 1972; **76**: 1147–1152.
- [7] Decarreau A. *Matériaux argileux : structure, propriétés et applications*. Société française de minéralogie et de cristallographie groupe français des argiles, Paris, 1990.
- [8] Skipper N, Lock P, Titiloye J, Swenson J, Mirza Z, Howells W, Fernandez-Alonso F. The structure and dynamics of 2-dimensional fluids in swelling clays. *Chemical geology* 2006; **230**: 182–196.
- [9] Cases J, Bérard I, Besson G, François M, Uriot J, Thomas F, Poirier J. Mechanism of adsorption and desorption of water vapor by homoionic montmorillonite. 1. the sodium-exchanged form. *Langmuir* 1992; **8**: 2730–2739.
- [10] Walrafen G, Douglas R. Raman spectra from very concentrated aqueous NaOH and from wet and dry, solid, and anhydrous molten, LiOH, NaOH, and KOH. *The Journal of chemical physics*, 2006; **124**: 114504.
- [11] Rinnert E. *Etats d'hydratation d'argiles suivis par analyses vibrationnelles de l'eau et des hydroxyles dans le proche infrarouge : applications aux systèmes saponite et bentonite*, thèse de doctorat, Université Henri Poincaré Nancy 1, 2004.