



**HAL**  
open science

## Taking into account final mining wastes in LCA: How to quantify the impacts of tailings?

Stéphanie Muller, Arnault Lassin, F Lai, Sylvain Guignot

### ► To cite this version:

Stéphanie Muller, Arnault Lassin, F Lai, Sylvain Guignot. Taking into account final mining wastes in LCA: How to quantify the impacts of tailings?. LCM 2019, Sep 2019, Poznan, Poland. hal-02154855

**HAL Id: hal-02154855**

**<https://brgm.hal.science/hal-02154855>**

Submitted on 4 Oct 2019

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



# Taking into account final mining wastes in LCA: How to quantify the impacts of tailings?

S. Muller<sup>1</sup>, A. Lassin<sup>1</sup>, F.Lai<sup>1</sup>, S. Guignot<sup>1</sup>

LCM 2019

3<sup>rd</sup> September 2019

Session: Metals industry in a sustainable world – chances and challenges

1: BRGM




Géosciences pour une Terre durable


**brgm**

# Context and objectives: tailings generation

- Tailings: ground rock + process water that are generated in a mine processing plant
- In 2014: the EU generated more than 700 million tons of waste in the mining and quarrying sector
- This figure might increase
  - From 2003 to 2013: combined weighted decrease of copper ore grades was 25%
- Environmental impacts of tailings
  - Long term emissions
  - Associated risk



<https://www.wsj.com/articles/brazils-samarco-disaster-mining-dams-grow-to-colossal-heights-and-so-do-the-risks-1459782411>



Calvo et al., 2016




<https://watchers.news/2019/01/26/tailings-dam-collapse-brumadinho-minas-gerais-brazil/>

## Tailings considerations in LCA

- Few LCA studies focus specifically on tailings management
  - Have access to **site-specific data**
    - Leaching obtained by standard tests (Song et al., 2017) or lab experiments (Reid et al. 2009)
  - Tailings management contribute the most to **human toxicity** and **marine ecotoxicity** when include in metal production (Song et al., 2017)
  - Tailings impacts contribution highly depends on **temporal perspective** (Beylot and Villeneuve, 2017)
- When looking at theecoinvent database
  - All metal production datasets model tailings based on the same unit processes
    - Only uncertainty factors differ to take into account the context of the dataset
  - Distinction between sulfidic and non sulfidic tailings

## Developed by Gabor Doka for landfills and adapted for tailings impoundments (Doka, 2008, 2009 and 2017)




Expression of transfert coefficients following a first order kinetics equation:

$$TK(t) = TK_{\infty} \left[ 1 - \exp \left( - \frac{V_{eff} * c_0}{m * TK_{\infty}} * t \right) \right]$$

with  $TK_{\infty}$ : fraction of the observed element (in the solid) that can be emitted (100% by default)

and  $V_{eff}$ : Effective leachate volume (depends on climatic conditions, tailings height and density)



### Developed by Gabor Doka for landfills and adapted for tailings impoundments (Doka, 2008, 2009 and 2017)

- Generic transfert coefficients determined for each element based on literature data
- Development of an « average » tailings, with:
  - an average initial tailings composition
  - an average initial leaching concentration
  - average tailings and meteorological characteristics
  - the assumption that all metals are leached on an infinite time frame
- Huge uncertainty factors are associated to the generic transfer coefficients
- Developed based on a first order kinetics that do not consider all physical and chemical interactions occurring in the tailings and in the surroundings

## A tool to assess long-term tailings emissions

Reactive transport modeling aims at understanding the distribution in space and time of chemical reactions occurring in a specific environment

Depends on mass transport, heat transport and geochemical reactions

Development of databases and softwares


Thermodynamics (mass action laws):  
 $AB \leftrightarrow A^+ + B^-$  with  $K = [A^+][B^-]/[AB]$

Kinetics:  
 $dm_{AB}/dt = k e^{-E/RT} (1 - [A^+][B^-]/K)$



**K** (aqueous species, minerals, gases)  
**k, E** (minerals)

Databases

Fluid flows & mass transport




Chemical interactions



## Case study: Presentation and specific data acquisition

- Emissions resulting from the treatment of 1 kg of sulfidic tailings on a 100 years timeframe
  - resulting from the exploitation of a copper-nickel ore body in Europe

- Comparison between:




- Site specific data obtained from:
  - The mine operator
    - Climatic conditions, hydraulic properties
  - Sampling campaigns on the mine site
    - Tailings composition, water composition



## Original tailings composition

Element	Symbol	mass (g_element / kg_tailings)
Sulfur	S ●	5.24
Copper	Cu	5.20
Silicon	Si	197.11
Iron	Fe	159.14
Calcium	Ca	91.11
Aluminium	Al	12.34
Potassium	K	4.29
Magnesium	Mg	87.72
Sodium	Na	0.60

Mineral 1



Mineral 2




## 1D column of tailings

- To estimate the flows of chemical compounds at the outlet of the tailings
- Geochemical calculation code = **PhreeqC** with **Thermoddem**  
(Thermodynamic and kinetic database: <http://thermoddem.brgm.fr/>)

### Conceptual model

Simulation over a period of 100 years  
(1200 time steps)

100 cells  
Total length ~ 2m



#### Input

Rainwater:

- net infiltration:  $10^{-8}$  m/s
- O<sub>2</sub>, CO<sub>2</sub>, pH

In every cell:

- Tailings mineralogy
- Groundwater chemistry
- Porosity


#### Output:

- Aqueous concentrations
- Mineralogical evolution

*PhreeqC: Parkhurst and Appelo (2013)*  
*Thermoddem: Blanc et al. (2012)*

# Resulting transfert coefficients – 100 years timeframe


## TK(100) - Leaching fraction after 100 years



- Overall, generic data overestimate the simulated leached fraction
- Differences between calculated and simulated values can be explained by the consideration of kinetics and thermodynamics
- Differences between generic and calculated data come from site specific considerations


# Differences that have an impact on resulting emissions

Emissions on a 100 years timeframe :  $m_e * TK(100)$



- Generic value, as in ecoinvent
- Generic transfer coefficients, specific waste composition
- Calculated transfer coefficients, specific waste composition
- Simulated value

## For a more realistic estimation of the emissions



And then:

- Consideration of a **longer temporal perspective**
- Resulting emissions and **associated impacts compared** to the whole life cycle of metals production

- Tailings emissions depend on:
  - Tailings composition
  - Characteristics of the surroundings (climatic conditions, water and soil properties, groundwater flow,....)
  - Generic values may overestimate the emissions especially when considering a specific temporal perspective
- Reactive transport modelling can provide more reliable results....
  - By accounting for the influence of the chemical reactivity of the elements
- ... But rely on on-site specific data
  - Hydraulic properties
  - Tailings composition and tailings pond geometry
  - Climatic conditions,...

- If emissions are site-specific, so are characterization factors
  - Generic and regional characterization in USEtox might differ by some orders of magnitude
  - A “groundwater” compartment is missing in USEtox
  - Only few metal species are characterized (Cu, Al and Fe)
- How these potential emissions compare themselves to existing legal limits (e.g. drinking water limits)?
- These are emissions when the mine closure is well managed, risks considerations are not taken into account here

- Integrated Mineral Technologies for More Sustainable Raw Material Supply
- Addresses H2020 issue “Sustainable selective low impact mining”
- 3 years: 1.6.2017 – 31.5.2020
- 7.9 M€ budget
- 16 partners



**Project’s ambition:** to develop and obtain a new paradigm proof of concept at mines sites to:

- recycle water
- value tailings
- improve environmental and economic results to enable future sustainable mineral supply in Europe.



Beylot, A., Villeneuve, J., 2017. Accounting for the environmental impacts of sulfidic tailings storage in the Life Cycle Assessment of copper production: A case study. *J. Clean. Prod.* 153, 139–145.

Blanc, P., Lassin, A., Piantone, P., Azaroual, M., Jacquemet, N., Fabbri, A., Gaucher, E.C., 2012. Thermoddem: A geochemical database focused on low temperature water/rock interactions and waste materials. *Applied Geochemistry* 27, 2107-2116.

Doka, G. 2008. “Life cycle inventory data of mining waste: Emissions from sulfidic tailings disposal”. Doka Life Cycle Assessments, Zürich, Switzerland

Doka G. 2009 3Life cycle inventories of waste treatment services. ecoinvent report No 13. Swiss center for Life cycle inventories, Dübendorf, 2009

Doka G. 2017. “A model for waste-specific and climate-specific life cycle inventories of tailings impoundments. Doka Life Cycle Assessments, Zürich, Switzerland

Guiomar Calvo, Gavin Mudd, Alicia Valero, and Antonio Valero. 2016. “Decreasing Ore Grades in Global Metallic Mining: A Theoretical Issue or a Global Reality?” *Resources* .  
<https://doi.org/10.3390/resources5040036>.

Parkhurst, D.L., Appelo, C.A.J., 2013. Description of input and examples for PHREEQC version 3: a computer program for speciation, batch-reaction, one-dimensional transport, and inverse geochemical calculations, *USGS Techniques and Methods*, Reston, VA, p. 519.

Song, X., Pettersen, J.B., Pedersen, K.B., Røberg, S., 2017. Comparative life cycle assessment of tailings management and energy scenarios for a copper ore mine: A case study in Northern Norway. *J. Clean. Prod.* 164, 892–904.



# Taking into account final mining wastes in LCA: How to quantify the impacts of tailings?

S. Muller<sup>1</sup>, A. Lassin<sup>1</sup>, F.Lai<sup>1</sup>, S. Guignot<sup>1</sup>

Thank you for your attention

[s.muller@brgm.fr](mailto:s.muller@brgm.fr)

[a.lassin@brgm.fr](mailto:a.lassin@brgm.fr)

1: BRGM



This Project has received funding from the European Union H2020 programme under grant agreement n° 730480



Géosciences pour une Terre durable

**brgm**