

Optimization of iridium oxy-hydroxide films for pH monitoring of underground components of nuclear repositories

Romain Rodrigues, Ioannis Ignatiadis, Johan Bertrand, Stéphanie Betelu

► To cite this version:

Romain Rodrigues, Ioannis Ignatiadis, Johan Bertrand, Stéphanie Betelu. Optimization of iridium oxy-hydroxide films for pH monitoring of underground components of nuclear repositories. 8th International Conference on Clays in Natural and Engineered Barriers for Radioactive Waste Confinement, Jun 2022, Nancy, France. hal-03642131v1

HAL Id: hal-03642131 https://brgm.hal.science/hal-03642131v1

Submitted on 14 Apr 2022 (v1), last revised 22 Jun 2022 (v2)

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Optimization of iridium oxy-hydroxide films for pH monitoring of underground components of nuclear repositories

Romain Rodrigues¹, Ioannis Ignatiadis^{1*}, Johan Bertrand², <u>Stéphanie Betelu^{1*}</u>

¹ BRGM, French Geological Survey, Orléans; *<u>i.ignatiadis@brgm.fr</u>, <u>s.betelu@brgm.fr</u>

² ANDRA, French national radioactive waste management agency, Châtenay Malabry, France

Keywords: pH sensor, iridium oxy-hydroxide, super-Nernstian response.

For the long-term monitoring of the pore water of clay-based disposal systems, the development of robust all-solid pH sensors, which do not necessitate any maintenance, is required. Due to their high stability, corrosion resistance and reversible redox properties, iridium oxyhydroxides (IrOx) are widely investigated for pH sensing and can be regarded among the promising technologies to be devoted to the observation and monitoring of pH of underground components of nuclear repositories.

This work aimed at in depth investigating and optimizing the IrOx coating process for pH measurements in agreement with the specific constraints related to on-site conditions. Electrochemically assisted synthesis was selected in order to control the oxidation states of IrOx redox active species in the coating.

The first objective was to give insights into the mechanism of electrodeposition of IrOx film on gold- or platinum-coated electrodes (S=0.198 cm²) by coupling electrochemistry with quartz crystal microbalance (QCM) measurements and scanning electronic microscopy (SEM) with energy dispersive X-ray spectroscopy (EDS). Electro-assisted syntheses were performed using an Ir^(IV)-based salt solution which was prepared according to [1]. Linear sweep voltammetry (LSV) and cyclic voltammetry (CV) identified both Ir^(III)/Ir^(IV) and Ir^(IV)/Ir^(V) as well as O₂/H₂O and OH⁻/O₂ redox couples involved at the electrode interface during the electro-assisted synthesis (Fig. 1a). The coupling of QCM with LSV, CV, chronopotentiometry (CP) or chronoamperometry (CA) provided results clarifying the different physical and chemical processes associated to redox reactions occurring at the electrode (Fig. 1b).

The second objective of this study was to determine the sensitivity and stability of the IrOxbased sensor depending on the electrochemically assisted synthesis technique and methodology. Electro-generation of IrOx-coatings were performed on carbon-based screenprinted electrodes (SPEs), which allow quick generation of reliable data [2]. Measurements were conducted by potentiometric measurements at several pH in the range 4-12 at 25 °C, under atmosphere and in a glove box (GB, $pO_2 = 10^{-6}$ atm). These conditions were selected in agreement with those encountered in the environment of the nuclear repositories. Irrespective of the selected electrodeposition technique, IrOx films can exhibit a super-Nernstian response (> 59.2 mV/pH), depending on the electrodeposition time or sweep rate (Fig. 2). Among the different techniques tested, the more suitable to improve the sensitivity in the entire pH range are CP and CV, with slopes between -60 and -70 mV/pH (R² \geq 0.98). Electrochemical impedance spectroscopy measurements showed low corrosion rates, indicating the stability of IrOx films. They appear thus appropriate for the long-term monitoring of the pore water of nuclear waste repositories. Work is in progress to demonstrate the robustness of IrOx-based sensors in situ over a long period.

References:

- K. Yamanaka, Anodically electrodeposited iridium oxide films (AEIROF) from alkaline solutions for electrochromic display devices, Jpn. J. Appl. Phys. 28 (1989) 632–637.
- [2] J. Daoudi, S. Betelu, T. Tzedakis, J. Bertrand, I. Ignatiadis, A Multi-Parametric Device with Innovative Solid Electrodes for Long-Term Monitoring of pH, Redox-Potential and Conductivity in a Nuclear Waste Repository, Sensors 17 (2017) 1372.

Figure 1:

